



Angarsk Polymer Plant Joint Stock Company 665800, Irkutsk region, Angarsk, block 8, (Pervyi industrial area), building 5 e-mail: secr@azp.ru Tel.: 8(3955) 57-30-00, 57-30-02

The products were manufactured under control established in the integrated management system certified by Quality Austria in accordance with the requirements of ISO 9001:2015, ISO 14001:2015, ISO 45001:2018, ISO 50001:2018, Certificates Nos. 25613/0, 04306/0, 01144/0, and 00241/0

Testing Center, Central Factory Laboratory 665830, Irkutsk region, Angarsk, industrial zone. Angarsk Polymer Plant Joint Stock Company e-mail: ZabrodinaSV@azp.rosneft.ru Tel. 8(3955) 57-41-84 Certificate of Accreditation of the Testing Center, Central Factory Laboratory of AZP JSC No. ROSS

Validity period of the accreditation certificate: unlimited. **CERTIFICATE No. 2080**

High-pressure (low-density) polyethylene 10803-020, highest grade Export

Certificate of Conformity No. POCC RU C-RU.HP15.H08360/21 Valid until January 19, 2024

OKPD2 code 20.16.10.111

Batch number: 2184 Date of manufacture: August 21, 2021

Batch size (mass): 10.000 t

Sampling site (according to GOST 2517): Shop warehouse 122/123, facility 1083

Date of sampling: August 21, 2021 Test date: August 23, 2021

The certificate was issued on the basis of: test results dated August 23, 2021 No. 2080-ПВД108







				TOBAPUD 2020
No.	Name of indicator	Testing method	Norm according to GOST 16337- 77	Actual value
1	Mass fraction of the granules with a size from 1 to 2 mm, %, not more than	As to Item 3.8, GOST 16337-77	0.5	Absence
2	Mass fraction of the granules with a size from 5 to 8 mm, %, not more than	As to Item 3.8, GOST 16337-77	0.25	Absence
3	Mass fraction of gray and oxidized granules	As to Item 3.9, GOST 16337-77	Not allowed	Absence
4	Density, g/cm ³	As to Item 5, GOST 15139-69	0.9185 ± 0.0015	0.9172
5	Melt liquidity index (rated value) with tolerance, %, g/10 min	GOST 11645-73	2.0 ± 10	2.0
6	Diversity of the melt liquidity index within batch, %, not more than	As to Item 3.13, GOST 16337-77	± 5	±3
7	Number of inclusions, pcs., not more than	As to Item 3.14, GOST 16337-77	2	2
8	Process sample for the film external appearance	As to Item 3.15, GOST 16337-77	В	-
9	Cracking resistance, h, not less than	GOST 13518-68	2	4
10	Tensile yield point, Pa (kgf/cm²), not less than	GOST 11262-2017	93 * 10 ⁵ (95)	101*10^5 (103)
11	Tensile strength, Pa (kgf/cm²), not less than	GOST 11262-2017	122 * 10 ⁵ (125)	135*10^5 (138)
12	Tension set, %, not less than	GOST 11262-2017	550	604
13	Mass fraction of extractables, %, not more than	GOST-26393-84	0.9	0.6
14	Odor and taste of aqueous extracts, points, not more than	As to Item 2, GOST 22648-77	1	1

Conclusion:

High-pressure polyethylene 10803-020, highest grade complies with the requirements of:

- GOST 16337-77 with amendments 1-3 "High-Pressure Polyethylene, Grades. Specifications"

Additional Information:

- transportation and storage: as per Item 4, GOST 16337-77 with amendments 1–3;
- warranty period of storage: 3 year from the date of manufacture.
- Safety Data Sheet No. 46693089.20.47205 Valid until July 10, 2022.
- Container "Polyethylene Bag with Internal Lamination. (25 kg)"

Number of containers: 400 pcs.

Stamp here

Operator of the Section of Raw Material T.I. Molchanova **Preparation and Issue of Intermediates** and Products, 4th Category Certificate issue date:

(Power of Attorney No. A3Π-114/21 dated January 1, 2021) August 23, 2021